



2010 Self-Priming 100% Acrylic Latex Exterior Satin Gloss

402XX

Product Description:

2010 100% Acrylic Latex Exterior Satin Gloss is a medium gloss offering superior, durable, weather resistant finish and years of lasting protection. It levels beautifully to a smooth lustrous sheen with maximum breathability, color and gloss retention, alkali, mildew and fume resistance and long term flexibility. 2010 House Paint is self-priming over many new and previously painted surfaces. Specific primers are recommended for many new wood surfaces. 2010 represents the latest technology with superior hiding and application characteristics. It's the perfect coating for any exterior surface requiring a long lasting beautiful satin gloss finish.

Recommended Use:

Clapboards, shingles, shakes, trim, sash, alum./vinyl siding, shutters, masonry, doors, hardboard, primed metal.

Application:

WARNING! If you scrape, sand or remove old paint from any surface, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Carefully clean up with a wet mop or HEPA vacuum. Before you start, find out how to protect yourself and your family by contacting the U.S. EPA/Lead Information Hotline at 1-800-424-LEAD (5323) or log on to www.epa.gov/lead.

Surfaces must be clean and free of surface contaminants. On previously painted surfaces, remove all loose or scaly paint by sanding or scraping so that all remaining paint is tightly adhered to the surface. Spot prime all bare spots or badly eroded areas with Troubleshooter® 100% Acrylic Latex Primer or Universal Oil Wood Primer. All mildewed areas should be scrubbed with a solution of equal parts household bleach and water. Use rubber gloves and safety goggles for protection during application. Rinse thoroughly with clean water and allow to dry before painting. Excessively chalky, salty or dusty surfaces and all protected areas should be washed down with fresh water, then hosed clean. Caulk all holes and joints around windows, doors, trim, clapboards and other openings with California Caulking Compound. Thin sparingly with water only if necessary to obtain proper application consistency (1/2 pint per gallon). Spray application consistency can be achieved by reducing material with one pint of water to a gallon. Apply paint generously and uniformly. Do not brush out excessively. In hot weather work on shady side of building if possible. Material can be applied to a damp surface but excess surface moisture must be removed before painting. New Wood Shingles, Shakes, Clapboards, Trim, Plywood, Texture III - Spot prime knots and resin areas with Prime Choice® Oil Based Stain-Blocking Primer #20700 before priming entire surface with Troubleshooter Latex or Oil Wood Primer. If brown stains show through cedar or other redwoods after priming, spot prime again. Concrete, Masonry Block - Previously unfinished concrete or dense masonry block can be primed and finished using two coats of 2010 100% Acrylic Latex House Paint Satin Gloss Finish. Stucco, Cement, Asbestos, Siding, Brick - Unpainted but weathered or aged surfaces require a prime coat of Stonite Masonry Conditioner before finish painting. Ferrous Metal - All bare metal must be primed with Rust Stop® Rust Inhibiting Metal Primer. Aluminum or Vinyl Siding - 2010 100% Acrylic Latex House & Trim Paint Satin Gloss Finish can be applied directly to aluminum or vinyl siding that has been properly washed to remove the oxidation. Vinyl siding, however, can only be painted with white or light pastel colors, never darker than the color of the original vinyl siding.

Architectural Specifications:

- New Wood, Clapboards, Shingles, Shakes, Trim:
 - 1 Coat California Troubleshooter® Universal Oil Primer or 100% Acrylic Latex Primer
 - 1 or 2 coats California 2010 Exterior Satin Gloss Finish
 - New Stucco, Masonry or Cement Asbestos:
 - 2 coats California 2010 100% Acrylic Latex House & Trim Paint Satin Gloss Finish 402XX
 - Masonry Block, Porous Concrete:
 - 1 coat Mason-Cote® Block Filler 3751
 - 1 or 2 coats California 2010 100% Acrylic Latex House & Trim Paint Satin Gloss Finish 402XX
 - New Galvanized Metal (Downspouts, Facias, Gutters):
 - 2 coats California 2010 100% Acrylic Latex House & Trim Paint Satin Gloss Finish 402XX
 - Wood-Repaint:
 - 1 coat California 2010 100% Acrylic Latex House & Trim Paint Satin Gloss Finish 402XX
 - Aged Stucco, Masonry or Cement Asbestos:
 - 1 coat Stonite® Masonry Conditioner 7010
 - 1 or 2 coats California 2010 100% Acrylic Latex House & Trim Paint Satin Gloss Finish 402XX
 - Aluminum and Vinyl Siding:
 - 1 or 2 coats California 2010 100% Acrylic Latex House & Trim Paint Satin Gloss Finish 402XX
- Note: Use House Paint Primer Gray under dark colors. Spot prime if needed.

Precautions:

Do not mix with other paints, solvents or colors in oil. Keep from freezing. Air and surface temperature should be above 50° F during application and drying time. Do not paint when rain or dew is imminent. 2010 100% Acrylic Latex House & Trim Paint Eggshell Finish is resistant to the deteriorating action of mildew and bacteria. No claim is made for the preservative action to other than the paint film.

Safety Information:

Keep out of reach of children. Do not take internally. Close container after each use.

Product Specifications:

Type: 100% Acrylic Latex
Exposure: Exterior
Specular Gloss: 45 @ 60° ± 5
Volume Solids: 36.8 % ± 2
Solids by Weight: 50.2 % ± 2
Vehicle: 74.9 % ± 2
Pigment: 25.2 % ± 2
Dry Film Thickness: 1.4 mils
Viscosity @ 77 °F: 103KU ± 3
Maximum VOC: 150 g/liter
Flash Pt °F: Non-combustible
Thinner: Water
Clean Up: Soap & Water

Available Colors and Bases:

White	Pastel
Medium	Deep
Ultra Deep	Neutral

Available Package Sizes:

Quart Gallon 5 Gallon

(Weight Per Gallon: 10.7 lbs. ± .5 lb)

Drying Times:

To Touch: 2 hrs.
To Handle: 4 hrs.
To Recoat: 4 hrs.

(@ 70-77 °F, 50% R.H.)

Surface Spread Rate:

Smooth: 400-450 s.f./gal.
Porous: 300-350 s.f./gal.

(Spray Application is 50% of above)

Tools and Equipment:

Brush -
 Synthetic, Nylon or Polyester

Roller -
 3/8" Nap Synthetic Fiber

Airless Spray -
 .017 to .019 Tip