



Fres~Coat Self-priming 100% Acrylic Latex Satin 536XX

Product Description:

Fres~Coat 100% Acrylic Latex Satin Finish is a premium quality, extremely durable 100% acrylic latex satin-gloss enamel. The smooth flowing anti-spatter formula provides superior leveling, adhesion, color retention and scrubability. This product is self-priming over most substrates. It is the perfect finish for high use areas such as kitchens and baths in homes, corridors, service areas, classrooms and general surfaces in public buildings and institutions.

Recommended Use:

Plaster, sheetrock, wallboard, concrete, masonry block, wood, primed metal, galvanized metal.

Application:

WARNING! If you scrape, sand or remove old paint from any surface, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Carefully clean up with a wet mop or HEPA vacuum. Before you start, find out how to protect yourself and your family by contacting the U.S. EPA/Lead Information Hotline at 1-800-424- LEAD (5323) or log on to www.epa.gov/lead.

Surfaces to be painted must be free of dust, mildew, dirt, grease, loose paint, oil, glue size, calcimine, wax, soap, and other surface contamination. Patch irregularities with vinyl patching paste or an appropriate patching compound. Fres~Coat 100% Acrylic Latex Satin Finish is self-priming over bare sheetrock, composition board, ceiling tile and concrete.

Plaster, Veneer Plaster (Blueboard) - New plaster must be fully cured and should be wiped with a wet sponge to neutralize any "hot spots". The moisture content should be below 15%. Full plaster requires a minimum of 30 days, skim coat plaster a minimum of 10 days to cure. Nibs should be knifed off before painting. Do not sand until after the surface is painted.

Ferrous Metal - Clean, then prime with Rust Stop® Rust Inhibiting Metal Primer

New Wood - Knots and stains should be sealed with Prime Choice® Oil Based Stain-blocking Primer #20700 or Prime Choice Universal Latex Stain-blocking Primer #50600 to avoid staining. All wood should then be primed with California Prime Choice Alkyd Primer-sealer #20200 or Prime Choice Latex All Surface Primer #50300.

Masonry Block - Apply one coat of Mason-Cote® Block Filler 3751 if a denser surface is desired.

Architectural Specifications:

- Plaster, Wallboard, Sheetrock:
2 coats Fres~Coat 100% Acrylic Latex Satin Finish 536XX
- Concrete, Non-Porous Masonry:
2 coats Fres~Coat 100% Acrylic Latex Satin Finish 536XX
- Porous Masonry and Block:
1 coat Mason-Cote® Block Filler 3751
1 or 2 coats Fres~Coat 100% Acrylic Latex Satin Finish 536XX
- Ferrous Metal - Un-primed:
1 coat Rust Stop® Rust Inhibiting Metal Primer 21150
1 or 2 coats Fres~Coat 100% Acrylic Latex Satin Finish 536XX
- Ferrous Metal - Primed, Galvanized Metal:
2 coats Fres~Coat 100% Acrylic Latex Satin Finish 536XX
- Wood:
1 coat Prime Choice™ All Surface Acrylic Primer 50300 (see above comments on "New Wood")
1 or 2 coats Fres~Coat 100% Acrylic Latex Satin Finish 536XX
- Acoustical Tile:

Precautions:

Do not add solvents, oils or colors in oil, or mix with other paint types. Do not apply when air or surface temperature is below 50° F or when drying conditions are poor. Keep from freezing. Use adequate ventilation.

Safety Information:

Keep out of reach of children. Do not take internally. Close container after each use.

Product Specifications:

Type: 100% Acrylic Latex
Exposure: Interior
Specular Gloss: 28@ 60° ± 4
Volume Solids: 28.6 % ± 2
Solids by Weight: 41.7 % ± 2
Vehicle: 76.5 % ± 2
Pigment: 23.5 % ± 2
Dry Film Thickness: 1.3 mils
Viscosity @ 77 °F: 98KU ± 3
Maximum VOC: 150g/liter
Flash Pt °F: Non-combustible
Thinner: Water
Clean Up: Soap & Water

Available Colors and Bases:

White	Pastel
Medium	Deep
Ultra Deep	Neutral

Available Package Sizes:

Quart Gallon 5 Gallon

(Weight Per Gallon: 10.3 lbs. ± .5 lb)

Drying Times:

To Touch: 1 hrs.
To Handle: 8 hrs.
To Recoat: 4 hrs.

(@ 70-77 °F, 50% R.H.)

Surface Spread Rate:

Smooth: 325-375 s.f./gal.
Porous: 250-300 s.f./gal.

(Spray Application is 50% of above)

Tools and Equipment:

Brush -
Synthetic, Nylon or Polyester

Roller -
3/8" Nap Synthetic Fiber

Airless Spray -
.017 to .019 Tip