



Pro 2000® Acrylic Latex Semi-Gloss 558XX

Product Description:

PRO 2000 ACRYLIC LATEX SEMI-GLOSS is a smooth flowing latex semi-gloss enamel developed to provide an attractive, scrubbable finish for high use areas in schools, commercial and public buildings. This anti-spatter formulation, developed with the contractor in mind, dries quickly to a velvety smooth finish ideal for most interior surfaces.

Recommended Use:

Plaster, sheetrock, wallboard, concrete, masonry block, wood, primed metal, primed galvanized metal.

Application:

WARNING! If you scrape, sand or remove old paint from any surface, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Carefully clean up with a wet mop or HEPA vacuum. Before you start, find out how to protect yourself and your family by contacting the U.S. EPA/Lead Information Hotline at 1-800-424-LEAD (5323) or log on to www.epa.gov/lead.

Surfaces to be painted must be free of dust, mildew, dirt, grease, loose paint, oil, glue size, calcimine, wax, soap, and other surface contamination. Patch irregularities with vinyl patching paste or an appropriate patching compound. PRO 2000 ACRYLIC SEMI-GLOSS is self-priming over bare sheetrock, composition board, ceiling tile and concrete.

New Plaster - Knife off all nibs and protrusions. Wipe with a clean damp cloth to remove loose particles. Do not sand new plaster until it is primed.
Wallboard, Sheetrock, Gypsum Board - Joint compound should be sanded smooth, but avoid abrading the paper.
Ferrous Metal, Galvanized Metal - Clean, then prime with Larcoloid® Rust Inhibiting Metal Primer
Wood - Seal knots and stains with Prime Choice™ Low Odor Oil Base Primer Sealer or Prime Choice™ 100% Acrylic Universal Primer.
Masonry Block - Apply one coat of ProPaint Block Filler 51500 if a denser surface is desired.

Architectural Specifications:

- Plaster, Wallboard, Sheetrock:
2 coats Pro 2000 Acrylic Semi-Gloss 558XX
- Concrete, Non-Porous Masonry:
2 coats Pro 2000 Acrylic Semi-Gloss 558XX
- Porous Masonry and Block:
1 coat ProPaint® Block Filler 51500
1 or 2 coats Pro 2000 Acrylic Semi-Gloss 558XX
- Ferrous Metal - Un-primed:
1 coat Larcoloid® Rust Inhibiting Metal Primer 21150
1 or 2 coats Pro 2000 Acrylic Semi-Gloss 558XX
- Galvanized Metal:
1 coat Larcoloid Acrylic Latex Rust Inhibiting Metal Primer, White 51106, Gray 51108, Red 51107
1 or 2 coats Pro 2000 Acrylic Semi-Gloss 558XX
- Wood:
1 coat Prime Choice™ All Surface Acrylic Primer 50300
1 or 2 coats Pro 2000 Acrylic Semi-Gloss 558XX
- Acoustical Tile:
2 coats Pro 2000 Acrylic Semi-Gloss 558XX

Precautions:

Do not add solvents, oils or colors in oil, or mix with other paint types. Do not apply when air or surface temperature is below 50° F or when drying conditions are poor. Keep from freezing. Use adequate ventilation.

Safety Information:

Keep out of reach of children. Do not take internally. Close container after each use.

Product Specifications:

Type: Vinyl Acrylic Latex
Exposure: Interior
Specular Gloss: 45@ 60° ± 5
Volume Solids: 31.6 % ± 2
Solids by Weight: 43.0 % ± 2
Vehicle: 79.0 % ± 2
Pigment: 21.0 % ± 2
Dry Film Thickness: 1.4 mils
Viscosity @ 77 °F: 93 KU ± 5
Maximum VOC: 150 g/liter
Flash Pt °F: Non-combustible
Thinner: Water
Clean Up: Soap & Water

Available Colors and Bases:

White Pastel
Medium Deep
Neutral
Super Hide White

Available Package Sizes:

Gallon 5 Gallon

(Weight Per Gallon: 10.1 lbs. ± .5 lb)

Drying Times:

To Touch: 1 hrs.
To Handle: 8 hrs.
To Recoat: 4 hrs.
(@ 70-77 °F, 50% R.H.)

Surface Spread Rate:

Smooth: 350-400 s.f./gal.
Porous: 250-300 s.f./gal.
(Spray Application is 50% of above)

Tools and Equipment:

Brush -
Synthetic, Nylon or Polyester

Roller -
3/8" Nap Synthetic Fiber

Airless Spray -
.017 to .019 Tip