



Pacific® Self-Priming Interior Semi-Gloss
559XX

Product Description:

Pacific Semi-Gloss is a smooth flowing latex semi-gloss enamel developed to provide an attractive, scrubbable finish for high use areas in homes, schools, commercial and public buildings. This product is self-priming over most substrates. This anti-splatter formulation dries quickly to a velvety smooth finish ideal for most interior surfaces.

Recommended Use:

Plaster, sheetrock, wallboard, concrete, masonry block, wood, primed metal, primed galvanized metal.

Application:

WARNING! If you scrape, sand or remove old paint from any surface, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Carefully clean up with a wet mop or HEPA vacuum. Before you start, find out how to protect yourself and your family by contacting the U.S. EPA/Lead Information Hotline at 1-800- 424-LEAD (5323) or log on to www.epa.gov/lead.

Surfaces to be painted must be free of dust, mildew, dirt, grease, loose paint, oil, glue size, calcimine, wax, soap, and other surface contamination. Patch irregularities with vinyl patching paste or an appropriate patching compound. Pacific Semi-Gloss is self-priming over bare sheetrock, composition board, ceiling tile and concrete.

Plaster, Veneer Plaster (Blueboard) - New plaster must be fully cured and should be wiped with a wet sponge to neutralize any "hot spots". The moisture content should be below 15%. Full plaster requires a minimum of 30 days, skim coat plaster a minimum of 10 days to cure. Nibs should be knifed off before painting. Do not sand until after the surface is painted. It is preferable to prime new plaster with 100% Acrylic Primer such as Primer Choice 50300.
 Ferrous Metal - Clean, then prime with Rust Stop® Rust Inhibiting Metal Primer
 New Wood - Knots and stains should be sealed with Prime Choice® Oil Based Stain-blocking Primer #20700 or Prime Choice Universal Latex Stain-Blocking Primer #50600 to avoid staining. All wood should then be primed with California Prime Choice Alkyd Primer-sealer #20200 or Primer Choice Latex All Surface Primer #50300.
 Masonry Block - Apply one coat of Mason-Cote® Block Filler 3751 if a denser surface is desired.

Architectural Specifications:

- Plaster, Wallboard, Sheetrock: (It is preferable to prime new plaster with 100% Acrylic Primer such as Prime Choice 50300)
2 coats Pacific Semi-Gloss 559XX
- Concrete, Non-Porous Masonry:
2 coats Pacific Semi-Gloss 559XX
- Porous Masonry and Block:
1 coat Mason-Cote® Block Filler 3751
1 or 2 coats Pacific Semi-Gloss 559XX
- Ferrous Metal - Un-primed:
1 coat Rust Stop® 106X-Series Rust Inhibiting Metal Primer
1 or 2 coats Pacific Semi-Gloss 559XX
- Galvanized Metal:
1 coat Rust Stop® 106X-Series Rust Inhibiting Metal Primer
1 or 2 coats Pacific Semi-Gloss 559XX
- Wood:
1 coat Prime Choice™ All Surface Acrylic Primer 50300
1 or 2 coats Pacific Semi-Gloss 559XX
- Acoustical Tile:
2 coats Pacific Semi-Gloss 559XX

Precautions:

Do not add solvents, oils or colors in oil, or mix with other paint types. Do not apply when air or surface temperature is below 50° F or when drying conditions are poor. Keep from freezing. Use adequate ventilation.

Safety Information:

Keep out of reach of children. Do not take internally. Close container after each use.

Product Specifications:

Type: Vinyl Acrylic Latex
Exposure: Interior
Specular Gloss: 45@ 60° ± 5
Volume Solids: 31.8 % ± 2
Solids by Weight: 43.5 % ± 2
Vehicle: 79.1 % ± 2
Pigment: 20.9 % ± 2
Dry Film Thickness: 1.4 mils
Viscosity @ 77 °F: 93KU ± 3
Maximum VOC: 150 g/liter
Flash Pt °F: Non-combustible
Thinner: Water
Clean Up: Soap & Water

Available Colors and Bases:

White 7 Stock
 Pastel Medium
 Deep Neutral

Available Package Sizes:

Quart Gallon 5 Gallon

(Weight Per Gallon: 10.1 lbs. ± .5 lb)

Drying Times:

To Touch: 1 hrs.
To Handle: 8 hrs.
To Recoat: 4 hrs.

(@ 70-77 °F, 50% R.H.)

Surface Spread Rate:

Smooth: 400-450 s.f./gal.
Porous: 250-300 s.f./gal.

(Spray Application is 50% of above)

Tools and Equipment:

Brush -
Synthetic, Nylon or Polyester

Roller -
3/8" Nap Synthetic Fiber

Airless Spray -
.017 to .019 Tip