



ENVIROTECH Zero VOC 100% Acrylic Latex Eggshell 631XX*

Product Description:

ENVIROTECH ZERO VOC 100% Acrylic Latex Eggshell is a commercial grade, environmentally preferred interior paint with essentially no odor. The 100% acrylic latex formulation is smooth flowing with excellent application characteristics. High hiding and durable, ENVIROTECH Zero VOC dries to an attractive smooth finish that is washable and presents a uniform appearance. It is the perfect finish for high use areas such as kitchens, baths, corridors, service areas, classrooms and general surfaces in public buildings and institutions.

Recommended Use:

Plaster, sheetrock, wallboard, concrete, masonry block, wood, primed metal, galvanized metal, acoustical surfaces.

Application:

WARNING! If you scrape, sand or remove old paint from any surface, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Carefully clean up with a wet mop or HEPA vacuum. Before you start, find out how to protect yourself and your family by contacting the U.S. EPA/Lead Information Hotline at 1-800-424-LEAD (5323) or log on to www.epa.gov/lead.

Surface Preparation: Surfaces to be painted must be free of dust, mildew, dirt, grease, loose paint, oil, glue size, calcimine, wax, soap, and other surface contamination. Patch irregularities with vinyl patching paste or an appropriate patching compound. ENVIROTECH Zero VOC 100% Acrylic Latex Eggshell is self-priming over bare sheetrock, composition board, ceiling tile and concrete.

- New Plaster - Knife off all nibs and protrusions. Wipe with a clean damp cloth to remove loose particles. Do not sand new plaster until it is primed.
- Wallboard, Sheetrock, Gypsum Board - Joint compound should be sanded smooth, but avoid abrading the paper.
- Ferrous Metal - Clean, then prime with Larcoloid Rust Inhibiting Metal Primer
- Wood - Seal knots and stains with Wipe-Out, Wipe-Out Low Odor or Wipe-Out 100% Acrylic Stain Block or Stopz Masonry Block - Apply one coat of Mason-Cote Block Filler 3751 if a denser surface is desired.

Architectural Specifications:

- Plaster, Wallboard, Sheetrock:
 - 1 coat ENVIROTECH Zero VOC Interior 100% Acrylic Latex Primer-Sealer 64600 or
 - 2 coats ENVIROTECH Zero VOC 100% Acrylic Latex Eggshell 631XX
- Concrete, Non-Porous Masonry:
 - 2 coats ENVIROTECH Zero VOC 100% Acrylic Latex Eggshell 631XX
- Porous Masonry and Block:
 - 1 coat Mason-Cote® Block Filler 3751
 - 1 or 2 coats ENVIROTECH Zero VOC 100% Acrylic Latex Eggshell 631XX
- Ferrous Metal - Un-primed:
 - 1 coat Larcoloid® Rust Inhibiting Metal Primer 21150
 - 1 or 2 coats ENVIROTECH Zero VOC 100% Acrylic Latex Eggshell 631XX
- Ferrous Metal -Primed, Galvanized Metal:
 - 2 coats 2 coats ENVIROTECH Zero VOC 100% Acrylic Latex Eggshell 631XX
- Wood:
 - 1 coat ENVIROTECH Zero VOC Interior 100% Acrylic Latex Primer-Sealer 64600
 - 1 or 2 coats ENVIROTECH Zero VOC 100% Acrylic Latex Eggshell 631XX
- Acoustical Tile:
 - 2 coats ENVIROTECH Zero VOC 100% Acrylic Latex Eggshell 631XX

Precautions:

Do not add solvents, oils or colors in oil, or mix with other paint types. Do not apply when air or surface temperature is below 50° F or when drying conditions are poor. Keep from freezing.

Safety Information:

Keep out of reach of children. Do not take internally. Close container after each use.

* Specifications shown above are for 63191

Product Specifications:

Type: 100% Acrylic Latex
Exposure: Interior
Specular Gloss: 8 @ 60° ±2
Volume Solids: 35.8 % ±2
Solids by Weight: 53 % ±2
Vehicle: 64.2 % ±2
Pigment: 35.8 % ±2
Dry Film Thickness: 2 mils
Viscosity @ 77 °F: 77 KU ±5
Maximum VOC: Calc. 0g/liter
Flash Pt °F: Non-combustible
Thinner: Water
Clean Up: Soap & Water

Available Colors and Bases:

| | |
|---------|--------|
| White | Pastel |
| Medium | Deep |
| Neutral | |

Available Package Sizes:

Gallon 5 Gallon

(Weight Per Gallon: 11.4 lbs. ± .5 lb)

Drying Times:

To Touch: 1 hrs.
To Handle: 24 hrs.
To Recoat: 2 hrs.
 (@ 70-77 °F, 50% R.H.)

Surface Spread Rate:

Smooth: 275-300 s.f./gal.
Porous: N/A s.f./gal.
 (Spray Application is 50% of above)

Tools and Equipment:

- Brush -**
Synthetic, Nylon or Polyester
- Roller -**
3/8" Nap Synthetic Fiber
- Airless Spray -**
.017 to .019 Tip